

ARCHITECTURAL PVDF				STEEL				ALUMINUM			
COLOR	SR	IE	SRI	26GA. [¶]	24GA. [†]	22GA. ^{†▲}	18GA. ^{†▲}	.032" [†]	.040" [†]	.050" ^{†▲}	.063" ^{†▲}
Regal White	.70	.85	85		●■	●	●	●■			●
Bone White	.68	.86	82		●■	●	●	●■	●	●	
Almond	.63	.86	75		●■			●■	●	●	
Sandstone	.47	.86	53		●■	●		●	●	●	
Surrey Beige	.35	.86	37		●■	●		●	●	●	
Sierra Tan	.30	.85	30	LG	●■			●	●	●	
Medium Bronze	.26	.84	24	LG [^]	●■	●	●	●■	●	●	●
Mansard Brown	.29	.86	29		●■			●■	●	●	
Dark Bronze	.26	.84	25	LG [^]	●■	●	●	●■	●	●	●
Extra Dark Bronze	.05	.89	-1.0		●■			●		●	
Patina Green	.25	.87	24		●■			●			
Hemlock Green	.28	.87	28		●■						
Classic Green	.25	.86	24	LG	●■	●		●	●		
Hartford Green**	.10	.86	4.0	LG	●■			●		●	
Teal**	.28	.87	28		●						
Regal Blue**	.30	.86	30		●■			●			
Slate Blue	.27	.86	26	LG	●■			●			
Terra Cotta	.39	.85	42		●■						
Banner Red**	.44	.86	49		●■			●			
Colonial Red	.31	.86	31	LG	●■			●			
Brandywine**	.27	.87	27		●■			●			
Dove Gray	.49	.87	56		●■			●■		●	
Slate Gray	.37	.86	39	LG [^]	●■			●■	●		
Charcoal	.08	.90	4.0		●■	●		●■	●	●	
Matte Black	.26	.86	25	LG [^]	●■	●		●■	●	●	
Bright Silver++	.55	.77	61		●■			●■	●	●	
Silversmith++	.48	.80	52		●■			●			
Champagne++	.37	.83	38		●■			●			
Pewter++	.36	.85	38		●■			●			
Bright Copper++	.41	.85	44		●■			●■			
Stone White	.62	.85	73		●■			●	●		

PAINT PERFORMANCE PROPERTIES	HOT DIPPED GALVANIZED STEEL OR GALVALUME®	ALUMINUM
Accelerated Weathering ASTM D 4587 (Drew Cycle Weatherometer) ASTM G-154 Chalk Rating Per ASTM D 4214, Method A	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max Hours: 5,000 Total Chalk: Rating 6 Color: 5 Δ E Hunter units max	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max Hours: 5,000 Total Chalk: Rating 6 Color: 5 Δ E Hunter units max
Salt Spray ASTM B 117	Hours: 1,000 Total Scribe: Rating 1/16" (2mm) Field: Rating 10, no blisters	Hours: 3,000 Total Scribe: Rating 10, no creepage Field: Rating 10, no blisters
Humidity ASTM D 2247	Hours: 2,000 Total Rating: 10, no blisters Per ASTM D 714	Hours: 3,000 Total Rating: 10, no blisters Per ASTM D 714
Formability ASTM D 4145	0T-2T	0T-2T
ASTM D 522 (Elongation over 1/8" mandrel)	No cracking No loss of adhesion	No cracking No loss of adhesion
Pencil Hardness ASTM D 3363	HB-2H	HB-2H
Abrasion Resistance ASTM D 968	55-75 Liters of falling sand	55-75 Liters of falling sand
Specular Gloss ASTM D 523	30 +/- 5 at 60° 55 +/- 5 at 85°	30 +/- 5 at 60° 55 +/- 5 at 85°
Reverse Impact ASTM D 2794	2 x Metal thickness in inch-lbs. No loss of adhesion. No Cracking.	1/2 x Metal thickness in inch-lbs. No loss of adhesion. No cracking.
Flame Test ASTM E 84	Class A rated coating	Class A rated coating

† Standard Coil Width is 48.25"

‡ Standard Coil Width is 44.375"

● Standard Color Option.

■ 40.5" Coil Option is Available.

▲ Additional Lead Times May Apply.

¶ Standard Coil Width 40.5"

LG Refers to Reflective Ratings

^ Offered in 27-1/2" coil width

++ Denotes Mica Colors

** Denotes exotic colors and are subject to premium pricing

NOTES ON AVAILABILITY:

- 24ga, .032, .040, .050, .063 are standard 48.25" in width. 22g and 18ga are 44.375" in width. 26ga is 40.5" standard width for painted items.
- Protective stippable film is standard on flat sheets.
- Mica++ and exotics ** are subject to premium pricing. Due to the unique effect of the Mica finishes, appearances may vary from batch to batch.
- Standard inventory is non-embossed. Embossed requests are to be quoted.
- Unpainted, acrylic coated, aluminum-zinc alloy steel (AZ55) is maintained in 26ga 20", 26ga 27-1/2", 26ga 24", 24ga 20", 24ga 27-1/2", 24ga 24" slit coils and 26ga 48"x120", 24ga 48"x120" flat sheets (no strippable film).
- All colors are supplied in Medium Gloss (20-35 at 60 deg). Low gloss on non 26ga available subject to minimum coating run.
- This color chart is subject to change without notice.

SentriClad® standard architectural colors and finishes feature 70% polyvinylidene fluoride (PVDF) resin paint systems to ensure long term color retention and performance. Custom colors and finishes are also available. Minimum quantities and set up charges may apply.

877-495-7663 www.sentrigrad.com



PROUDLY FINISHED WITH
SHERWIN-WILLIAMS
Coil Coatings

SRI RATINGS ARE FOR GALVALUME ONLY.
ALUMINUM RATINGS ARE LISTED ON
WWW.SENTRIGARD.COM