



SENTRICLAD ARCHITECTURAL COLOR PALETTE

CORE COLORS



Regal White □
SR: .70 IE: .85 SRI: 85



Bone White □
SR: .68 IE: .86 SRI: 82



Stone White Δ
SR: .62 IE: .85 SRI: 73



Almond Δ
SR: .63 IE: .86 SRI: 75



Sandstone Δ
SR: .47 IE: .86 SRI: 53



Sierra Tan
SR: .30 IE: .85 SRI: 30



Medium Bronze
SR: .31 IE: .87 SRI: 24



Mansard Brown
SR: .29 IE: .86 SRI: 29



Dark Bronze
SR: .26 IE: .84 SRI: 25



Extra Dark Bronze-
SR: .05 IE: .89 SRI: -1



Patina Green
SR: .25 IE: .87 SRI: 24



Classic Green
SR: .25 IE: .86 SRI: 24



Dove Gray
SR: .49 IE: .87 SRI: 56



Slate Gray Δ
SR: .37 IE: .86 SRI: 39



Charcoal
SR: .32 IE: .86 SRI: 33



Matte Black
SR: .26 IE: .86 SRI: 25



True Black
SR: .05 IE: .89 SRI: -1



Slate Blue
SR: .30 IE: .87 SRI: 31




Terra Cotta
SR: .39 IE: .85 SRI: 42



Colonial Red
SRI: .31 IE: .86 SRI: 31



Brandywine **
SR: .27 IE: .87 SRI: 27




Regal Blue **
SR: .30 IE: .86 SRI: 30




Banner Red **
SR: .44 IE: .86 SRI: 49



Teal **
SR: .28 IE: .87 SRI: 28



Hartford Green - **
SR: .10 IE: .86 SRI: 4



Silversmith S15** .+
SR: .48 IE: .80 SRI: 52



Champagne S20 ** .+
SR: .37 IE: .83 SRI: 38



Pewter S11** .+
SR: .36 IE: .85 SRI: 38



Bright Copper Δ S25** .+
SR: .41 IE: .85 SRI: 44



Bright Silver Δ S66 ** .+
SR: .55 IE: .77 SRI: 61



Aged Copper Metallic ** .+
SR: .25 IE: .85 SRI: 23

Colors within the gray boxes are subject to premium pricing.

.+ Featuring a pearlescent mica finish; subject to premium pricing. Colors shown are as close to actual colors as allowed by the printing process. Actual metal samples are available. Colors may appear different when viewed at different angles and under different lighting conditions. Due to product improvements, changes, and other factors we reserve the right to change or delete information herein without prior notice.

** Denotes Exotic Colors and are Subject to Premium Pricing

Acrylic Coated Galvalume also available (not pictured).

26 GAUGE LOW GLOSS COLORS



Sierra Tan
SR: .46 IE: .87 SRI: 52



Slate Gray
SR: .37 IE: .86 SRI: 39



Medium Bronze
SR: .31 IE: .87 SRI: 32



Dark Bronze
SR: .28 IE: .86 SRI: 27



Colonial Red
SR: .31 IE: .87 SRI: 31



Regal White
SR: .71 IE: .86 SRI: 86



Dove Gray
SR: .48 IE: .86 SRI: 54



Classic Green
SR: .31 IE: .87 SRI: 32



Hartford Green **
SR: .08 IE: .09 SRI: 4



Slate Blue
SR: .30 IE: .87 SRI: 31



Matte Black
SR: .26 IE: .86 SRI: 25



Mansard Brown
SR: .29 IE: .86 SRI: 29




Bone White
SR: .73 IE: .86 SRI: 89




Terra Cotta
SR: .40 IE: .87 SRI: 44



Charcoal
SR: .08 IE: .90 SRI: 4.0



Bright Silver ** .+
SR: .55 IE: .77 SRI: 61



Bright Copper ** .+
SR: .41 IE: .85 SRI: 44

SR= Solar Reflectivity IE= Initial Emissivity SRI= Solar Reflective Index

Please check website for the most up to date SR, IE, and SRI values.

□ LEED® compliant for low slope and steep slope
Δ LEED® compliant for steep slope only

PVDF- 70% polyvinylidene fluoride resin paint system

Use our visualizer to see our colors on your roof or walls!



Upload a picture of your property to find the perfect color. Scan the QR code above to get started.

ARCHITECTURAL PVDF				STEEL				ALUMINUM			
COLOR	SR	IE	SRI	26GA.	24GA. †	22GA.‡	18GA.‡▲	.032" †	.040" †	.050" †	.063" †▲
Regal White	.70	.85	85	LG^	●■	●	●▲	●■	●	●	●▲
Bone White	.68	.86	82	LG^	●■	●	●▲	●■	●	●	●▲
Stone White	.62	.85	73		●■			●■	●		
Almond	.63	.86	75		●■			●■	●	●	
Sandstone	.47	.86	53		●■	●		●■	●	●	
Sierra Tan	.30	.85	30	LG^	●■			●■	●	●	●▲
Medium Bronze	.26	.84	24	LG^	●■	●	●▲	●■	●	●	●▲
Mansard Brown	.29	.86	29	LG^	●■			●■	●	●	
Dark Bronze	.26	.84	25	LG^	●■	●	●▲	●■	●	●	●▲
Extra Dark Bronze	.05	.89	-1.0		●■			●■		●	
Patina Green	.25	.87	24		●■			●■	●		
Classic Green	.25	.86	24	LG^	●■	●		●■	●		
Hartford Green **	.10	.86	4.0	LG	●■			●■		●	
Teal **	.28	.87	28		●■			●■▲			
Slate Blue	.26	.86	25	LG^	●■			●■	●		
Regal Blue **	.28	.87	28		●■			●■	●		
Terra Cotta	.39	.85	42	LG^▲	●■			●■			
Banner Red **	.44	.86	49		●■			●■			
Colonial Red	.31	.86	31	LG	●■			●■			
Brandywine **	.27	.87	27		●■			●■▲			
Dove Gray	.49	.87	56	LG^	●■			●■	●▲		
Slate Gray	.37	.86	39	LG^	●■			●■	●	●	
Charcoal	.32	.86	33	LG^	●■	●		●■	●	●	●▲
Matte Black	.26	.86	25	LG^	●■	●		●■	●	●	●▲
True Black	.05	.89	-1.0		●■			●■			
Bright Silver ++	.55	.77	61	^	●■			●■	●	●	
Silversmith ++	.48	.80	52		●■			●■			
Champagne ++	.37	.83	38		●■			●■			
Pewter ++	.36	.85	38		●■			●■			
Bright Copper ++	.41	.85	44	^	●■			●■			
Aged Copper Metallic ++	.25	.85	23		●■			●■			

PAINT PERFORMANCE PROPERTIES		HOT DIPPED GALVANIZED STEEL OR GALVALUME™	ALUMINUM
Accelerated Weathering ASTM D 4587 (Drew Cycle Weatherometer) ASTM G-154 Chalk Rating Per ASTM D 4214, Method A		Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max Hours: 5,000 Total Chalk: Rating 6 Color: 5 Δ E Hunter units max	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max Hours: 5,000 Total Chalk: Rating 6 Color: 5 Δ E Hunter units max
Salt Spray ASTM B 117		Hours: 1,000 Total Scribe: Rating ⅛" (2mm) Field: Rating 10, no blisters	Hours: 3,000 Total Scribe: Rating 10, no creepage Field: Rating 10, no blisters
Humidity ASTM D 2247		Hours: 2,000 Total Rating: 10, no blisters per ASTM D 714	Hours: 3,000 Total Rating: 10, no blisters per ASTM D 714
Formability ASTM D 4145		OT- 2T	OT- 2T
ASTM D 522 (Elongation over ⅛" mandrel)		No cracking No loss of adhesion	No cracking No loss of adhesion
Pencil Hardness ASTM D 3363		HB-2H	HB-2H
Abrasion Resistance ASTM D 968		55-75 Liters of falling sand	55-75 Liters of falling sand
Specular Gloss ASTM D 523		30 +/- 5 at 60° 55 +/- 5 at 85°	30 +/- 5 at 60° 55 +/- 5 at 85°
Reverse Impact ASTM D 2794		2 x Metal thickness in inch-lbs. No loss of adhesion. No cracking.	1/2 x Metal thickness in inch-lbs. No loss of adhesion. No cracking.
Flame Test ASTM E 84		Class A rated coating	Class A rated coating

- † Standard Coil Width is 48.25"
- ‡ Standard Coil Width is 22 Ga 48.25", 18 Ga 44.375"
- Standard Color Option
- 40.5" Coil Option is Available
- ▲ Additional Lead Times May Apply
- LG Refers to Reflective Ratings
- ^ Offered in 27.5" Coil Width
- ++ Denotes Mica Colors and are Subject to Premium Pricing
- ** Denotes Exotic Color and are Subject to Premium Pricing

SHERWIN-WILLIAMS.
Coil Coatings
SRI RATINGS ARE FOR GALVALUME ONLY.
ALUMINUM RATINGS ARE LISTED ON
WWW.SENTRIGARD.COM
**** PLEASE REFER TO SENTRIGARD.COM
FOR THE MOST UP TO DATE COLOR
LISTING AND AVAILABILITY.****

- NOTES ON AVAILABILITY
1.

24 Ga .032, .040, .050, .063 are standard 48.25" in width. 22 Ga 48.25" and 18 Ga 44.375" in width. 26 Ga is 40.5" standard width for painted items.
2.

Protective strippable film is standard on all flat sheets
3.

Mica and exotics are subject to premium pricing. Due to the unique effect of the Mica finishes, appearances may vary from batch to batch.
4.

Standard delivery is non-embossed. Embossed requests are to be quoted.
5.

Unpainted, acrylic coated, aluminum-zinc alloy steel (AZ55) is maintained in 26 Ga 20", 26 Ga 27 ½", 26 Ga 24", 24 Ga 20", 24 Ga 27 ½", 24 Ga 24" slit coils and 26 Ga 48"x120", 24 Ga 48"x120" flat sheets (no strippable film).
6.

All colors are supplied in Medium Gloss (20-35 at 60 deg.). Low gloss on non 26GA available subject to a minimum coating run.
7.

This color chart is subject to change without notice.

Sentriclad® standard architectural colors and finishes feature 70% polyvinylidene fluoride (PVDF) resin paint systems to ensure long-term color retention and performance. Custom colors and finishes are also available. Minimum quantities and set up charges may apply.

877-495-7663 www.sentricgard.com